

Novagard® RTV 600-200

Specification Data



DESCRIPTION

Novagard RTV 600-200 is a two-component, platinum catalyzed gel.

APPLICATIONS

A silicone gel for potting and encapsulating, embedding, and coating intricate electronic components that may also be used as an adhesive for bonding dissimilar substrates. Product offers the following attributes:

- *Wide range of compatibility*
- *Low shrinkage*
- *Cures without inhibition*

INSTRUCTIONS

This material is shipped in separate containers that are labeled Part A and Part B. While the material may be mixed by hand, it is more appropriate to use automated, meter-mixing equipment as the work life is extremely short and the ultimate cure time is exceedingly fast. The compound is designed with a 1:1 volume:volume mix ratio. Automated mixing equipment eliminates the need for a deaeration cycle. If mixing by hand, weigh 50 parts of Part A into an appropriately sized mixing vessel; add 50 parts of Part B and mix thoroughly.

STORAGE

Novagard RTV 600-200 may be stored in the original unopened containers at, or below, 80°F for up to six (6) months.

AVAILABILITY

Novagard RTV 600-200 is available in 5 gallon pails or 55 gallon drums.

PRECAUTIONS

Do not estimate weights and measures. The product is mix ratio sensitive and requires accurate metering (1 part A:1 part B v/v). Part A is slightly moisture sensitive and will begin to cure and skin over if left exposed for prolonged periods.

GENERAL PROPERTIES

BEFORE CURE

Physical Property	Test Method	Performance Range
Appearance	After mixing	Clear
Mix Ratio	Base:Cure (by volume)	1:1
Specific Gravity	Mixed, 25°C Part A Part B	0.95 – 1.05 0.95 – 1.05
Viscosity	Mixed, 25°C Part A Part B	2,000 – 4,000 cPs 2,000 – 4,000 cPs
Working Time	Mixed, 25°C	<15 minutes
Cure Time		2 – 3 hours

AFTER CURE (7 Days at 25°C / 50% RH)*

Physical Property	Test Method	Typical Value
Penetration	Internal Test Method	4.0 – 4.3 mm
Pull	Internal Test Method	3.5 – 4.75 inches

* The values outlined reflect testing that was conducted under laboratory conditions, actual results may vary. The information provided in the above table is not intended for use in preparing specifications. Please consult manufacturer for additional information.

ADDITIONAL INFORMATION

Novagard believes that the information provided is a true and accurate description of the typical characteristics of the aforementioned product; however, it is the responsibility of the individual user to thoroughly test the product in their specific application to determine performance, efficacy and safety.